

# Technical data sheet with Mid sole

Ref : 70804 S3 POWER FLEX

CE Attestation N° : 0075/020/161/08/17/1266

Extension code : 09/09/17

Revision date : 20/04/2009

<u>THE SOLE</u>			<u>THE UPPER</u>		
	MTS	Norm		MTS	Norm
Resistance to shock			<i>Colour</i> NOIR	<i>Thickness</i> 20/22	1.5
Clear space in mm at impact	16.00	>=14	Material used	Crazy black	
Resistance to crushing			Resistance to tearing	Yes	>120
Clear space in mm under 15000N of constraint	18.00	>=14	Permeability to water vapor (mg/cm2.h)	4.80	>0.8
Conformity of the staples	Yes	Yes	Water vapor facor (mg/cm2)	46.10	>15
Sole width in mm	9.40	>4	Leather acidity (pH)	3.75	>3.2
Staple height in mm	3.40	>2	Time or the water to pass through in minutes	120	60
Resistance of tearing in kN/m	11.70	>8	Quantity of water absobed in % after 1h	15.00	<30
Resistance to abrasion : density	1.05	>0.9	Difference index	0.04	<0.7
Resistance to abrasion : loss of volume (mm3)	15.00	<150	<u>THE LINING OF THE FRONT PART</u>		
Hydrolysis (increase of the notch in mm after 150.000 flexions)	0.00	<6	Material used	DOUBLURE ARTICO	
Resistance to hydrocarbons (Increase in volume in %)	1.20	<12	Thickness	1	0.8
Necessary force to perfore the sole (N)	1200	>=1100	Abrasion : testing in dry atmosphere	> 25600	25600
Conformity of the sole	Yes	Yes	Abrasion : testing in humid atmosphere	> 12800	12800
Conformity of the mid-sole dimensions	Yes	Yes	Permeability to water vapor (mg/cm2.h)	88	>2
Antistatism : resistance to dry atm. (megaohms)	85	0.1<V<1000	Water vapor factor (mg/cm2)	701	>20
Antistatism : resistance to humid atm. (megaohms)	19	0.1<V<1000	<u>THE INSOLE</u>		
Heel shock absorber	36	>20		2.8	2
Resistance of the upper/sole adherence (N/mm)	4.50	>4	insert Anti-perforation composite		
Slip resistance EN ISO 20345:A1 SRA Ceramic	0.43	>=0.32	Water absorption in %	80	>35
Slip resistance EN ISO 20345:A1 SRB Steel	0.23	>=0.18	Water desorption in %	96	>40
			Cycles needed to obtain the tearing of the surface	>400	400
			<u>THE SEWING THREAD</u> 100 % Polyamide		
			<u>THE LACES</u> 100 % Polyester - Embout en Acetate de Cellulose		

## Sole specification :

ANNIC S.A.S. 82250 LAGUEPIE Tél. : +33 (5) 63 30 21 01 - Fax : +33 (5) 63 31 40 18

Web : <http://www.mts-morethansafety.com> E-mail : [contact@morethansafety.com](mailto:contact@morethansafety.com)

S.A.S. au capital de 573.840 € - R.C. B778 115 436 - Siret 778 115 436 00017 - APE : 193 Z - TVA CEE : FR 95 778 115 436

## Model specification :