

# Technical data sheet without Mid sole

Ref : 15207 S2 CREON +

CE Attestation N° : 0075/020/161/01/09/0050

Extension code : 04/01/09

Revision date : 28/01/2005

<u>THE SOLE</u>	MTS	Norm
Resistance to shock		
Clear space in mm at impact	16.00	>14
Resistance to crushing		
Clear space in mm under 15000N of constraint	16.00	>14
Conformity of the staples	Yes	Yes
Sole width in mm	4.00	>4
Staple height in mm	4.00	>2.5
Resistance of tearing in kN/m	15.00	>8
Resistance to abrasion : density	1.00	>0.9
Resistance to abrasion : loss of volume (mm <sup>3</sup> )	59.00	<150
Hydrolysis (increase of the notch in mm after 150.000 flexions)	0.00	<6
Resistance to hydrocarbons (Increase in volume in %)	0.00	<12
Necessary force to perform the sole (N)		
Conformity of the sole	Yes	Yes
Conformity of the steel mid-sole dimensions	Yes	Yes
Antistatism : resistance to dry atm. (megaohms)	700	0.1<V<1000
Antistatism : resistance to humid atm. (megaohms)	10	0.1<V<1000
Heel shock absorber	28	>20
Resistance of the upper/sole adherence (N/mm)	4.60	>4
Slip resistance EN ISO 20345:A1 SRA Ceramic	0.55	>=0.32
Slip resistance EN ISO 20345:A1 SRB Steel	0.31	>=0.18

<u>THE UPPER</u>	MTS	Norm
Colour blanc		
Thickness	2.0/2.2	1.5
Material used	art ON MICRO 2.0 blanc	
Resistance to tearing	Yes	>120
Permeability to water vapor (mg/cm <sup>2</sup> .h)	2.10	>0.8
Water vapor factor (mg/cm <sup>2</sup> )	19.60	>15
Leather acidity (pH)		
Time or the water to pass through in minutes	120	60
Quantity of water absorbed in % after 1h	8.00	<30
Difference index	0.00	<0.7

<u>THE LINING OF THE FRONT PART</u>		
Material used	Non tissé aiguilleté blanc	
Thickness	1.1	0.8
Abrasion : testing in dry atmosphere	>25600	25600
Abrasion : testing in humid atmosphere	>12800	12800
Permeability to water vapor (mg/cm <sup>2</sup> .h)	24	>2
Water vapor factor (mg/cm <sup>2</sup> )	189	>20

<u>THE INSOLE</u>	2.2	2
Matériau Cellulosique (mm)		
Water absorption in %	81	>35
Water desorption in %	99	>40
Cycles needed to obtain the tearing of the surface	>400	400

THE SEWING THREAD 100 % Polyamide

THE LACES 100 % Polyester - Embout en Acetate de Cellulose

## Sole specification :

ANNIC S.A.S. 82250 LAGUEPIE Tél. : +33 (5) 63 30 21 01 - Fax : +33 (5) 63 31 40 18

Web : <http://www.mts-morethansafety.com> E-mail : [contact@morethansafety.com](mailto:contact@morethansafety.com)

S.A.S. au capital de 573.840 € - R.C. B778 115 436 - Siret 778 115 436 00017 - APE : 193 Z - TVA CEE : FR 95 778 115 436